



HEMPEL'S CUSTOM MARINE POLISH 67445

Description:	HEMPEL'S CUSTOM MARINE POLISH 67445 is a liquid cleaning polish.
Recommended use:	For cleaning, polishing and protecting fibre.glass, painted and varnished surfaces.
Availability:	Part of European Yacht assortment. Local availability subject to confirmation.
PHYSICAL CONSTANTS:	
Shade nos/Colours:	09990/ Off-white.
Flash point:	49 °C [120.2 °F]
Specific gravity:	1 kg/litre [8 lbs/US gallon]
Dry to handle:	10 minute(s) at 20°C/68°F 20 minutes at 10°C/50°F
VOC content:	264 g/l [2.2 lbs/US gallon] <i>The physical constants stated are nominal data according to the HEMPEL Group's approved formulas.</i>
APPLICATION DETAILS:	
Safety:	Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult HEMPEL Safety Data Sheets and follow all local or national safety regulations.
SURFACE PREPARATION:	Wash surface thoroughly with HEMPEL'S PRE-CLEAN 67602 or HEMPEL'S BOAT SHAMPOO 67284 to remove dirt and other contaminants, rinse with fresh water. Allow the surface to dry Surfaces in good condition: Apply the product on a dry surface. Deteriorated surfaces: Must be treated with: HEMPEL'S RUBBING LIQUID 69021 before application of the product.
APPLICATION CONDITIONS:	Shake well before use. Apply the product with a clean, dry soft cloth. Polish with circular movements using a clean cloth or use a polishing machine to obtain a high gloss finish. Change to clean cloths frequently. When machine polishing, use a new polishing pad and not a compound pad as this can create swirl marks.
SUBSEQUENT COAT:	None. Recommended systems are: HEMPEL'S WAX TecCel 69034 or HEMPEL'S WAX 69033.
REMARKS:	
Application(s)	Do not apply in strong sunshine, on hot surfaces or under humid conditions. The surface temperature should be above: 5°C/41°F. When used on "metallic" paints, a test polishing on a less visible area is recommended. Allow freshly painted surfaces to dry/cure for at least 90 days before applying the product. Allow the protective film of the product to cure for at least 1 week before any detergent wash. The product cannot be removed by ordinary washing. Use HEMPEL'S PRE-CLEAN 67602 as instructed, rinse with fresh water.
Note:	HEMPEL'S CUSTOM MARINE POLISH 67445 The information given in the Product Data Sheet is intended for commercial use.
ISSUED BY:	HEMPEL A/S 6744509990

This Product Data Sheet supersedes those previously issued.

For explanations, definitions and scope, see "Explanatory Notes" available on www.hempel.com. Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.

The Products are supplied and all technical assistance is given subject to HEMPEL's GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice and become void five years from the date of issue.